

ABSTRACT

An elastic fabric comprising a crosslinked polyolefin fiber, wherein the fabric has retractions both in warpwise and weftwise directions of the fabric of 8 % or less after  
5 treated by dry heat at 65°C for 30 minutes is disclosed. Also disclosed is a process for producing an elastic fabric, comprising: retracting a fabric comprising a crosslinked polyolefin fiber while dyeing the fabric, and then  
10 stretching or relaxing the fabric at a stretch ratio of 15 % or less to finish the fabric with heat-setting.

The present invention relates to an elastic fabric having an excellent chemical resistance and an excellent dimensional stability in the form of a product, which is  
15 suitably used for sporting fabrics such as swimming suits, leotards and the like, inner fabrics for ladies as well as outer fabrics, for example.